

APPLICATION DATA SHEET

BLACKFAST 800 INTERSTAGE RUST INHIBITOR

Use: Blackfast 800 is used at 2-4% in water.
The recommended operating temperature is 50 - 60°C.
Agitate the components during immersion.
Dwell times 5 minutes.

Application: Blackfast 800, is used to protect components, after treatment with the Blackfast 181, to allow certain machining and assembly procedures to be carried out before treatment with Blackfast rust preventative 833, 841 or 933.

The product is compatible with alloy materials, cast iron, and with sensitive metals i.e. aluminium and zinc diecast.
Blackfast 800 offers protection up to 3 days.

Product safety data sheet: A safety data sheet is available.

Blackfast 800 is part of the Blackfast range of products for the treatment of iron, steel and aluminium at low temperatures.

Blackfast Chemicals continues to improve the quality and performance of its range of products and reserves the right to modify product formulations without prior notice.

OCTOBER 2002